



Product Close-up

EJ 1650 Description: This PTFE/fiberglass composite is designed for challenging insulation jacketing applications.

- ⇒ **Successfully used in insulation jacketing service since 1985.**
- ⇒ **Special coating technology for industrial fabrication.**
- ⇒ **Severe chemical and temperature exposure capabilities.**
- ⇒ **Variations engineered upon request.**
- ⇒ **Easily sewn.**
- ⇒ **Flame retardant.**



Special Colors Available

EJ 1650 Properties:

Upper Use Temperature: 550°F (287°C) Continuous Service

Weight: 16.5 oz/yd² (560 g/m²)

Thickness: 0.017" (0.43 mm)

Width: 60" (1524 mm) Nominal

Tensile Strength (Warp): 410 lbs/in (3664 N/50 mm)

Tensile Strength (Fill): 355 lbs/in (3173 N/50 mm)