



Product Close-up

***FLUOROTEX 100* Description:** This Perfluoroplastic/fiberglass composite is engineered for sealing applications in above ground storage tanks.

- **Successfully used in tank sealing service since 1987.**
- **Easily heat-sealed in field service.**
- **Severe chemical and temperature exposure capabilities.**
- **Variations in color, conductivity and coating engineered upon request.**

***FLUOROTEX 100* Properties:**

Upper Use Temperature: 600°F (316°C) Continuous Service

Weight: 13 oz/yd² (441 g/m²)

Thickness: 0.009" (0.23 mm)

Width: 38" (965 mm) Typical

Tensile Strength (Warp): 250 lbs/in (2234 N/50 mm)

Tensile Strength (Fill): 200 lbs/in (1787 N/50 mm)

FLUOROTEX is a trademark of **TEXTILES COATED INCORPORATED**.

This information is supplied in good faith and is based on information currently available. **TCI** makes NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTIES FOR FITNESS, OR USE FOR A PARTICULAR PURPOSE, OR OF ANY MERCHANTABILITY OR AGAINST INFRINGEMENT OR THE LIKE, unless expressly set forth herein.