



**Product Close-up**

***FLUOROTEX 300* Description:** This Perfluoroplastic/fiberglass composite is engineered for sealing applications in above ground storage tanks.

- **Successfully used in tank sealing service since 1987.**
- **Easily heat-sealed in field service.**
- **Severe chemical and temperature exposure capabilities.**
- **Variations in color, conductivity and coating engineered upon request.**

***FLUOROTEX 300* Properties:**

***Upper Use Temperature:*** 600°F (316°C) Continuous Service

***Weight:*** 19 oz/yd<sup>2</sup> (644 g/m<sup>2</sup>)

***Thickness:*** 0.014" (0.36 mm)

***Width:*** 60" (1524 mm) Typical

***Tensile Strength (Warp):*** 325 lbs/in (2905 N/50 mm)

***Tensile Strength (Fill):*** 275 lbs/in (2485 N/50 mm)

***FLUOROTEX*** is a trademark of **TEXTILES COATED INCORPORATED**.

This information is supplied in good faith and is based on information currently available. **TCI** makes NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTIES FOR FITNESS, OR USE FOR A PARTICULAR PURPOSE, OR OF ANY MERCHANTABILITY OR AGAINST INFRINGEMENT OR THE LIKE, unless expressly set forth herein.