


2.94 lbs/sq yd of PTFE
 (1,67 kg/sq m of PTFE)

PO Box 532/105 Rt. 101A Amherst, NH 03031 (603) 883-9932 FAX (603) 883-9956 www.textilecoated.com




TEXCOAT 1400: PTFE/Fiberglass composite with success in expansion joint service since 1987.

LFP 2120 CrossFilm Corrosion Liner

Physical Properties:

Weight: 30 oz/yd² (984 g/m²)
 Thickness: 0.020" (0.51 mm)
 Tensile Strength: 87 lb/in (778 N/50 mm)
 Tear Strength: 65 lb (295 N)

Each film ply in this picture has been given a different color to emphasize the multi-directional layering of the **CrossFilm**.




* Cross-section picture.
 ** Different colored plies are used with the TEX-LFP 14-20 Expansion Joint material for clarity in the photo.

TEX-LFP 14-20 CrossFilm Description:

An award-winning 0.020" (0.51 mm) LFP **CrossFilm** is laminated to a **TEXCOAT 1400** Load Bearing Component. The LFP **CrossFilm** is a 100% PTFE material that is capable of resisting the stress-cracking caused by flexing and severe temperature fluctuation in expansion joint applications. The multi-directional strength and durability of LFP allows it to function as a thick PTFE barrier for corrosive chemicals while maintaining a crack-free and flexible surface. The pictures above show the two components not laminated for half the sample. The toughness of the LFP **CrossFilm** is proven by the successful performance of the material in many industrial applications as a "stand-alone" product.

CrossFilm Technology: Breakthrough technology now permits thick PTFE liners to be used in expansion joint service without the fear of stress cracking due to severe operating conditions. As witnessed by the



chart, LFP is a different perfluoroplastic altogether. Ensure safety by using thick **CrossFilm** Technology and see why one judge for Chemical Processing's Vaaler Award concluded, "This is the first major improvement in the fluoroplastic industry since its introduction some 40-odd years ago."

TEX-LFP 14-20 CrossFilm Properties:

Materials of Construction:	Woven Fiberglass; Fluoropolymer Resins
Upper Use Temperature:	600°F (316°C) Continuous
Chemical Resistance:	Excellent
Weight:	80 oz/yd ² (2720 g/m ²)
Thickness:	0.060" (1.52 mm)
Width:	56" (1422 mm) to 59" (1498 mm); Special Widths Available
Tensile Strength:	Warp- 1200 lbs/in (10724 N/50 mm) Fill- 1200 lbs/in (10724 N/50 mm)

LFP, TEX-LFP, **CrossFilm**, and **TEXCOAT** are trademarks of **TEXTILES COATED INCORPORATED**.

Patents worldwide.

This information is supplied in good faith and is based on information currently available. TCI makes NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTIES FOR FITNESS, OR USE FOR A PARTICULAR PURPOSE, OR OF ANY MERCHANTABILITY OR AGAINST INFRINGEMENT OR THE LIKE, unless expressly set forth herein.