


PO Box 532/105 Rt. 101A Amherst, NH 03031 (603) 883-9932 FAX (603) 883-9956 [www.textilecoated.com](http://www.textilecoated.com)



**TEXCOAT 700:** PTFE/Fiberglass composite with success in expansion joint service since 1987.

**LFP 2109 *CrossFilm* Corrosion Liner**

**Physical Properties:**

Weight: 13.5 oz/yd<sup>2</sup> (458 g/m<sup>2</sup>)  
 Thickness: 0.009" (0.23 mm)  
 Tensile Strength: 25 lb/in (223 N/50 mm)  
 Tear Strength: 22 lb (99.8 N)

Each film ply in this picture has been given a different color to emphasize the multi-directional layering of the ***CrossFilm***.




\* Cross-section picture.  
 \*\* Different colored plies are used with the TEX-LFP 7-7 Expansion Joint material for clarity in the photo.

**TEX-LFP 7-7 *CrossFilm* Description:**

An award-winning 0.009" (0.23 mm) LFP ***CrossFilm*** is laminated to a **TEXCOAT 700** Load Bearing Component. The LFP ***CrossFilm*** is a 100% PTFE material that is capable of resisting the stress-cracking caused by flexing and severe temperature fluctuation in expansion joint applications. The multi-directional strength and durability of LFP allows it to function as a thick PTFE barrier for corrosive chemicals while maintaining a crack-free and flexible surface. The pictures above show the two components not laminated for half the sample. The toughness of the LFP ***CrossFilm*** is proven by the successful performance of the material in many industrial applications as a "stand-alone" product.

***CrossFilm* Technology:** Breakthrough technology now permits thick PTFE liners to be used in expansion joint service without the fear of stress cracking due to severe operating conditions. As witnessed by the chart, LFP is a different perfluoroplastic altogether. Ensure safety by using thick ***CrossFilm*** Technology and see why one judge for Chemical Processing's Vaaler Award concluded, "This is the first major improvement in the fluoroplastic industry since its introduction some 40-odd years



**TEX-LFP 7-7 *CrossFilm* Properties:**

<b>Materials of Construction:</b>	Woven Fiberglass; Fluoropolymer Resins
<b>Upper Use Temperature:</b>	600°F (316°C) Continuous
<b>Chemical Resistance:</b>	Excellent
<b>Weight:</b>	45 oz/yd <sup>2</sup> (1526 g/m <sup>2</sup> )
<b>Thickness:</b>	0.037" (0.94 mm)
<b>Width:</b>	56" (1422 mm) to 59" (1498 mm); Special Widths Available
<b>Tensile Strength:</b>	Warp- 700 lbs/in (6256 N/50 mm) Fill- 700 lbs/in (6256 N/50 mm)

LFP, TEX-LFP, ***CrossFilm***, and **TEXCOAT** are trademarks of **TEXTILES COATED INCORPORATED**.

Patents worldwide.

This information is supplied in good faith and is based on information currently available. TCI makes NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTIES FOR FITNESS, OR USE FOR A PARTICULAR PURPOSE, OR OF ANY MERCHANTABILITY OR AGAINST INFRINGEMENT OR THE LIKE, unless expressly set forth herein.