



\*(Films are red in this photo to show contrast)

***TS 103/2* Description:** This PTFE/fiberglass composite is engineered for wet or dry service in above ground storage tanks. PTFE films are laminated to both sides of the composite for enhanced protection in wet environments.

- **Successfully used in tank sealing service since 1987.**
- **Severe chemical and temperature exposure capabilities.**
- **Color, conductivity and width variations engineered upon request.**
- **Easily heat-sealed in field service.**

## ***TS 103/2* Properties:**

<b><i>Upper use temperature:</i></b>	600°F continuous (316°C)
<b><i>Weight:</i></b>	19 oz/yd <sup>2</sup> (644 g/m <sup>2</sup> )
<b><i>Thickness:</i></b>	0.015" (0.38 mm)
<b><i>Width:</i></b>	38" (965 mm) Typical; Cut-To-Size Widths Available Upon Request
<b><i>Tensile strength (Warp):</i></b>	250 lbs/in (2234 N/50 mm)
<b><i>Tensile strength (Fill):</i></b>	200 lbs/in (1787 N/50 mm)