



*(Film is red in this photo to show contrast)

TS 303 Properties:

TS 303 Description: This PTFE/fiberglass composite is engineered for wet or dry service in above ground storage tanks. A film is laminated to one side of the composite for enhanced protection in wet environments.

- **Successfully used in tank sealing service since 1987.**
- **Severe chemical and temperature exposure capabilities.**
- **Color, conductivity and width variations engineered upon request.**
- **Easily heat-sealed in field service.**

Upper use temperature:	600°F continuous (316°C)
Weight:	22 oz/yd ² (746 g/m ²)
Thickness:	0.017" (0.43 mm)
Width:	60" (1524 mm) Typical; Cut-To-Size Widths Available Upon Request
Tensile strength (Warp):	325 lbs/in (2905 N/50 mm)
Tensile strength (Fill):	275 lbs/in (2458 N/50 mm)