



**Product Close-up**

**TEXTIFILM 1404 Description:** **TEXTIFILM 1404** is engineered for dry, gas seal service. A 0.004" (0.1 mm) PTFE film is laminated to the **TEXCOAT 1400** product.

- ⇒ **Successfully used in expansion joint service since 1990.**
- ⇒ **Proven coating and lamination technology for industrial fabrication.**
- ⇒ **Severe chemical and temperature exposure capabilities.**
- ⇒ **Variations engineered upon request.**



**Many  
Colors  
Available**

**TEXTIFILM 1404 Properties:**

*Upper Use Temperature:* 600°F (316°C) Continuous Service

*Weight:* 52 oz/yd<sup>2</sup> (1763 g/m<sup>2</sup>)

*Thickness:* 0.044" (1.12 mm)

*Width:* 58" (1473 mm) Nominal

*Tensile Strength (Warp):* 1200 lbs/in (10724 N/50 mm)

*Tensile Strength (Fill):* 1200 lbs/in (10724 N/50 mm)

**TEXTIFILM** is a trademark of **TEXTILES COATED INCORPORATED**.

This information is supplied in good faith and is based on information currently available. TCI makes NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTIES FOR FITNESS, OR USE FOR A PARTICULAR PURPOSE, OR OF ANY MERCHANTABILITY OR AGAINST INFRINGEMENT OR THE LIKE, unless expressly set forth herein.