



TEXFILM™ 1009 Expansion Joint Material

LAMINATED PTFE/FIBERGLASS COMPOSITES ENGINEERED FOR MODERATE GAS SEAL SERVICE

TEXFILM™ 1009 Description:

TEXFILM™ 1009 is a non-porous composite consisting of a PTFE coated fiberglass fabric and a CrossFilm™ barrier, which has been laminated to one side of the fabric.

The woven fiberglass fabric was produced using continuous filament, plied, yarns. To the fabric was applied a uniform, durable, PTFE coating.

Three high strength plies of PTFE film were laminated to produce the CrossFilm™ barrier. The resulting 0.009 in. (0.23 mm) thick PTFE barrier is durable, flexible, and stress crack resistant.

This cost effective expansion joint material has been engineered for moderate duty flue gas service.



- Severe chemical and temperature exposure capabilities
- Variations available upon request
- TEXFILM™ has been successfully used in expansion joint service since 1990
- Proven coating and lamination technology for industrial fabrication

TEXFILM™ 1009 PROPERTIES

Materials of Construction:	Woven Fiberglass; Fluoropolymer Resins
Upper Use Temperature:	600°F (316°C) Continuous
Weight:	55 oz/yd ² (1870 g/m ²)
Thickness:	0.045" (1.14 mm)
Width:	60" (1524 mm)
Tensile Strength (Warp):	1000 lbs/in (8756 N/50 mm)
Tensile Strength (Fill):	1000 lbs/in (8756 N/50 mm)

TEXFILM™ and CrossFilm™ are trademarks of Textiles Coated International. This information is supplied in good faith and is based on information currently available. TCI makes NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTIES FOR FITNESS, OR USE FOR A PARTICULAR PURPOSE, OR OF ANY MERCHANTABILITY OR AGAINST INFRINGEMENT OR THE LIKE, unless expressly set forth herein.

TEXTILES COATED INTERNATIONAL | Manufacturer of High Performance PTFE Composites and Laminates

200 Bouchard Street, Manchester, NH 03103 PHONE: (603) 296-2221 FAX: (603) 296-2248 www.textilecoated.com