



# Hybrid™ 8.0 Insulation Jacketing Material

## PTFE LAMINATE ENGINEERED FOR EXTREME REMOVABLE INSULATION SERVICE

### Hybrid™ 8.0 Description:

This CrossFilm™ laminate is designed for the most challenging insulation jacketing applications at a pricing level that is competitive with typical dip-coated materials. In many high-temperature and industrial applications, Hybrid is generally regarded as a material that lasts more than three times longer than dip-coated materials.

Using a proprietary hybrid of PTFE film and fiberglass, this material will simulate an all-PTFE laminate with the stretch and minimal elongation of a fiberglass reinforcement. Unlike traditional PTFE-coated fiberglass insulation jacketing materials, which contain approximately 25% PTFE and 75% fiberglass, Hybrid contains 75% PTFE and 25% fiberglass.

With adhesion values that are significantly greater than dip-coated materials, Hybrid has a highly wear-resistant surface with minimal fiberglass fraying at material edges. It has higher excursion temperature capability than dip-coated materials and it is heat-sealable. The tent-like texture and flexibility makes it advantageous for the sewing or heat-sealing of removable insulation jacketing applications.



- Lasts more than three times longer than typical PTFE dip-coated products in high-temperature and industrial applications
- Competitive in price to dip-coated materials
- Contains 75% PTFE
- Higher adhesions than dip-coated materials gives greater wear resistance

- Minimal fiberglass fraying at material edges with minimal airborne fiberglass
- Higher excursion temperatures than dip-coated materials
- Heat-sealable
- Excellent flexibility and tear resistance
- Flame resistant
- Color, thickness, conductivity and width variations are available upon request

### HYBRID™ 8.0 TYPICAL PHYSICAL

<b>Upper Use Temperature:</b>	600°F (316°C) Continuous Service
<b>Thickness:</b>	0.0085 inches (0.216 mm)
<b>Width:</b>	60 inch (1524 mm); Cut-to-size widths available
<b>Weight:</b>	8.0 oz/yd <sup>2</sup> (271 (g/m <sup>2</sup> ))
<b>Tensile Strength (Warp):</b>	55 lbs/inch (482 N/50 mm)
<b>Trapezoidal Tear (Warp):</b>	20 lbs (89 N)

Patents pending. Hybrid™ and CrossFilm™ are trademarks of TEXTILES COATED INTERNATIONAL. This information is supplied in good faith and is based on information currently available. These values are based on preliminary test results and represent expected typical properties. TCI makes NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTIES FOR FITNESS, OR USE FOR A PARTICULAR PURPOSE, OR OF ANY MERCHANTABILITY OR AGAINST INFRINGEMENT OR THE LIKE, unless expressly set forth herein.