

LAMINATED PTFE/FIBERGLASS COMPOSITES ENGINEERED FOR MODERATE GAS SEAL SERVICE

TEXFILM™ 1005 Expansion Joint Material:

TEXFILM[™] 1005 is a nonporous composite consisting of a PTFE-coated fiberglass fabric and a CrossFilm[™] barrier, which has been laminated to one side of the fabric.

A durable PTFE coating has been applied to a rugged, continuous-filament fiberglass reinforcement. Three plies of high strength PTFE film were laminated to produce the CrossFilm™ barrier. The resulting 0.005 in (0.13 mm) thick PTFE barrier is rugged, flexible, and stress crack resistant.

This cost-effective expansion joint material has been engineered for moderate duty flue gas service.

 TEXFILM[™] has been successfully used in expansion joint service since 1990



- Proven coating and lamination technology for industrial fabrication
- Severe chemical and temperature exposure capabilities
- Product variations available upon request

TEXFILM™ 1005 PROPERTIES

Upper Use Temperature: 600°F (316°C) Continuous Service

Weight: 50 oz/yd² (1700 g/m²)

Thickness: 0.042" (1.06 mm)

Width: 60" (1524 mm)

Tensile Strength (Warp): 1000 lbs/in (8756 N/50 mm)

Tensile Strength (Fill): 1000 lbs/in (8756 N/50 mm)

TEXFILM™ and CrossFilm™ are trademarks of Textiles Coated International. This information is supplied in good faith and is based on information currently available. TCI makes NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTIES FOR FITNESS, OR USE FOR A PARTICULAR PURPOSE, OR OF ANY MERCHANTABILITY OR AGAINST INFRINGEMENT OR THE LIKE, unless expressly set forth herein.

TEXTILES COATED INTERNATIONAL | Manufacturer of High-Performance Fluoropolymer Films, Laminates, and Composites