


LAMINATED PTFE MATERIALS ENGINEERED FOR TANK SEALING SERVICE

TS™ 303-2 Conductive Tank Seal Material:

TS 303-2 Conductive is engineered for both wet and dry service in above ground storage tanks. PTFE films, 0.003" (0.08 mm) thick, are laminated to both sides of a high strength fiberglass textile containing a uniform, penetrating, PTFE coating. This nonporous laminate is capable of withstanding severe stresses in challenging environmental conditions.



Red films have been used in the photo to more clearly display the laminate components.



- Successfully used in tank sealing service since 1987
- Severe chemical and temperature exposure capabilities
- Nonporous
- Special variations, including special widths, available upon request
- Easily heat-sealed in field service

TS™ 303-2 CONDUCTIVE PROPERTIES

Upper Use Temperature: 600°F (316°C) Continuous Service

Weight: 21.5 oz/yd² (731 g/m²)

Thickness: 0.016" (0.41 mm)

Width: 60" (1524 mm) Typical

Tensile Strength (Warp): 325 lbs/in (2846 N/50 mm)

Tensile Strength (Fill): 275 lbs/in (2408 N/50 mm)

Surface Resistivity: < 300,000 ohms/sq

This information is supplied in good faith and is based on information currently available. TCI makes NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTIES FOR FITNESS, OR USE FOR A PARTICULAR PURPOSE, OR OF ANY MERCHANTABILITY OR AGAINST INFRINGEMENT OR THE LIKE, unless expressly set forth herein.