

PTFE/FIBERGLASS COMPOSITES ENGINEERED FOR DRY GAS SERVICE

TEXCOAT[™] 100:

This PTFE/fiberglass composite is engineered for high temperature, mechanically demanding expansion joint service.

- Successfully used in expansion joint service since 1990
- Incorporates proven TEXCOAT™ coating technology for industrial fabrication
- High temperature exposure capabilities
- Variations engineered upon request



TEXCOAT[™] 100 PROPERTIES

Upper Use Temperature:	600°F (316°C) Continuous Service
Weight:	13 oz/yd² (441 g/m²)
Thickness:	0.009" (0.23 mm)
Width:	60" (1524 mm); Cut-to-size widths available
Tensile Strength (Warp):	250 lbs/in (2189 N/50 mm)
Tensile Strength (Fill):	200 lbs/in (6129 N/50 mm)

TEXCOAT[™] is a trademark of TEXTILES COATED INCORPORATED. This information is supplied in good faith and is based on information currently available. TCI makes NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTIES FOR FITNESS, OR USE FOR A PARTICULAR PURPOSE, OR OF ANY MERCHANTABILITY OR AGAINST INFRINGE-MENT OR THE LIKE, unless expressly set forth herein.

TEXTILES COATED INTERNATIONAL | Manufacturer of High-Performance Fluoropolymer Films, Laminates, and Composites